


F - 2001

Flame Retardants®

Chemical name:	Brominated Epoxy Polymer
Formula:	$C_3H_5O(C_{18}H_{16}O_3Br_4)_n C_{18}H_{15}Br_4O_2$
CAS Number:	68928-70-1
%Br:	49-51
MW:	2300



General & Use:

For health & safety matters please refer to MSDS

Typical Properties

Epoxy Equivalent gr/eq	485-545
Color Gardner Dioxane 40% Soln	2
Bromine Content %	49-51
Particle Size 97% less than (mm)	2
Melting Point °C	67-86
Specific Gravity	1.8

Thermogravimetric Analysis (10°C / min, air)

Weight Loss(%)	°C
1	280
5	320
10	340

Please note that the values indicated do not constitute specification limits. To obtain current specifications, refer to your local Sales Office/Representative or ICL-IP Head Office at address herein.

Storage and Handling:

Store in a dry, cool and well-ventilated area. Avoid exposure to moisture. Avoid exposure to heat and to sunlight.

For more information please contact your local ICL office.



Visit our Website: www.icl-group.com

For more information about our products and to place an order, please contact one of our regional sales offices.

Head Office

ICL-IP Ltd.
E-mail: frinfo@icl-group.com

Europe

ICL-IP Europe B.V.
E-mail: fr.europe@icl-group.com

North America and Mexico

ICL-IP America Inc.
E-mail: fr.nam@icl-group.com

South America

ICL-IP Brasil Ltda.
E-mail: fr.sam@icl-group.com

Asia Pacific China

ICL-IP China
E-mail: fr.china@icl-group.com

Japan

ICL-IP Japan Ltd.
E-mail: fr.japan@icl-group.com

Other Asia Pacific

ICL-IP Asia Ltd.
E-mail: fr.asia@icl-group.com

Other parts of the World

E-mail: frinfo@icl-group.com

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable as of the date of publication. However, no warranty is made as to the accuracy of and/or sufficiency of such information and/or suggestions as to the merchantability or fitness of the product for any particular purpose, or that any suggested use will not infringe any patent. Nothing herein shall be construed as granting or extending any license under any patent. Buyer must determine for itself, by preliminary tests or otherwise, the suitability of this product for its purposes, including mixing this product with other products. The information contained herein supersedes all previously issued bulletins on the subject matter covered.