

Phosflex[®] 41L


Phosflex[®]
Flame Retardant Plasticizers

Chemical Name: Isopropylated triphenyl phosphate ester

CAS #

Isopropylphenyl diphenyl phosphate 68937-41-7

Triphenyl phosphate 115-86-6



Overview

Phosflex[®] 41L is a substituted triaryl phosphate ester made exclusively from synthetic feedstock. It has excellent flame retarding characteristics, which are typical of the triaryls. This flame retarding efficiency permits back-blending with non-flame retarding plasticizers, resulting in favorable economics and wide flexibility to formulators.

While used primarily in PVC formulations, Phosflex[®] 41L finds compatibility and utility in other resin systems as well.

Typical Properties:

Physical appearance:	Clear, transparent liquid
Phosphorus content wt. %	8.3
Specific gravity 20°C/20°C	1.160
Density @ 20°C lbs/gal	9.7
Density @ 20°C kg/m ³	1160
Viscosity @ 25°C mPa.s	100
Acidity mg KOH/g	0.10
Water content wt. %	0.10
Color APHA	<75

Thermogravimetric Analysis

(10°C/min. in nitrogen):


2% wt. loss	203°C
5% wt. loss	222°C
10% wt. loss	238°C

Safety & Handling

Consult the Safety Data Sheet for this product.

Shipping Information

Available in bulk tank trucks, isocontainers, 2,500 lb totes, and 533 lb drums.



Visit our Website: www.icl-group.com

For more information about our products and to place an order, please contact one of our regional sales offices.

Head Office

ICL-IP Ltd.
E-mail: frinfo@icl-ip.com

Europe

ICL-IP Europe B.V.
E-mail: fr.europe@icl-ip.com

North America and Mexico

ICL-IP America Inc.
E-mail: fr.nam@icl-ip.com

South America

ICL-IP Brasil Ltda.
E-mail: fr.sam@icl-ip.com

Asia Pacific China

ICL-IP China
E-mail: fr.china@icl-ip.com

Japan

ICL-IP Japan Ltd.
E-mail: fr.japan@icl-ip.com

Other Asia Pacific

ICL-IP Asia Ltd.
E-mail: fr.asia@icl-ip.com

Other parts of the World

E-mail: frinfo@icl-ip.com

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable as of the date of publication. However, no warranty is made as to the accuracy of and/or sufficiency of such information and/or suggestions as to the merchantability or fitness of the product for any particular purpose, or that any suggested use will not infringe any patent. Nothing herein shall be construed as granting or extending any license under any patent. Buyer must determine for itself, by preliminary tests or otherwise, the suitability of this product for its purposes, including mixing this product with other products. The information contained herein supersedes all previously issued bulletins on the subject matter covered.